

**Product**
**Type**
**COUNTER RUST™ 6060**
**Rust Preventive – Metal Protection  
 Butyl Ester of an Oxidized Wax**
**Application**

Counter Rust 6060 is a partial butyl ester of an oxidized wax.

Counter Rust 6060 is highly polar and has high affinity for metal surfaces. Counter Rust 6060's chemical and physical properties make it an important component in the formulation of water displacing rust preventives, cutting and gear oils as well as oil and solvent soluble corrosion preventives.

**Typical Properties**

Test	Typical
Appearance	Brown, waxy solid
Specific gravity at 15.6° C	0.88
Total acid number, mg KOH/g	<15
Congeval melt point, °C	40

**Benefits**

- Economical ester intermediate for many products
- Highly polar for metal affinity
- Provides good lubricity and anti-wear properties by leaving a multi-molecular layer on metal surfaces
- Excellent metal wetter

**Storage and Handling**

Recommended Maximum Long Term Storage Temperature	Ambient
Flash Point	170°C

**Lockhart Chemical Company**

4302 James P Cole Boulevard - Flint, MI 48505

Phone: 810-789-8330 Fax: 1-810-789-3266

[www.lockhartchem.com](http://www.lockhartchem.com)

 email: [customerservice@lockhartchem.com](mailto:customerservice@lockhartchem.com)

**DISCLAIMER:** To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given