



Product	Type
----------------	-------------

COUNTER RUST™ 7056 Rust Preventive

Acid vapor corrosion inhibitor

Application

Counter Rust 7056 is a cost effective additive for the formulation of corrosion inhibitors. It is highly effective in protecting all types of steel surfaces including highly polished, bright and ground surfaces. It is soluble in aliphatic, low aromatic solvents and oils. It can be formulated to leave dry or softer tacky films.

Typical Properties

Test	Typical
Appearance	Dark Solid
Specific gravity at 15.6° C	0.93
Total acid number, mg KOH/g	40
Total saponification number, mg KOH/g	52

Suggested Formulations

As a rust preventive for protection of steel in storage against acid fumes, salt water fog and high humidity

Counter Rust 7056	5 -25%	Counter Rust 7056	5-10%
Mineral Spirits	Balance	Oil	Balance

As a corrosion inhibitor in metalworking fluids, wax emulsions and polishes

2-20% Counter Rust 7056 depending on the protection required

Storage and Handling

Recommended Maximum Long Term Storage Temperature*	Ambient
Recommended Minimum Temperature for Use	Ambient
Flash Point	>150° C COC

*Long term storage at temperatures above this may result in loss of performance.



Lockhart Chemical Company

4302 James P Cole Boulevard Flint, MI 48505

Phone: 1-810-785-7165 Fax:1-810-789-3266

www.lockhartchem.com

email: customerservice@lockhartchem.com

DISCLAIMER: To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given

Counter Rust is a Trademark of the Lockhart Chemical Company

11/1/2017