

**Product**
**Type**
**SulfoGel™ 200A**
**Metal Protection**
**High solids thixotropic overbased calcium sulfonate base**
**Application**

SulfoGel 200A is a high-solids, thixotropic overbased calcium sulfonate used as the main formulating component in hot-melt and high solids long term rust preventive coatings. It contains microscopic lamellar calcite (calcium carbonate) platelets. SulfoGel 200A is in a hydrocarbon oil carrier.

**Typical Properties**

Test	Typical
Appearance	Viscous fluid
Pounds per gallon @25° C	8.5
Total base number, mg KOH/g	180
Brookfield RTV viscosity @ 25° C	140,000
Non-volatile, wt. %	>97
Water, wt. %	<1

**Benefits**

- Exceptional corrosion protection in salt environments
- Highly resistant to chloride induced corrosion
- Excellent surface wetting agent
- Low VOC starting material for long term rust preventive coatings
- Provide excellent rheology and anti-sag properties

**Storage and Handling**

Recommended Max Long Term Storage Temperature	Ambient
Flash Point	>175 ° C

**Lockhart Chemical Company**

4302 James P Cole Boulevard Flint, MI 48505

Phone: 1-810-789-8330 Fax:1-810-789-3266

[www.lockhartchem.com](http://www.lockhartchem.com) email: [customerservice@lockhartchem.com](mailto:customerservice@lockhartchem.com)

**DISCLAIMER:** To the best of our knowledge, the information and recommendations contained herein are accurate. However, this information and recommendations are furnished without any warranty, representation or license of any kind. Users of our products are encouraged to run their own tests to ensure product fitness for their applications. Furthermore, users assume sole liability for any patent infringement that occurs by reason of following our recommendations or using the information given